

Washed Concrete Sand

Sieve: *ASTM C33*

Size	% Passing
3/8"	100
#4	95-100
#8	80-100
#16	50-85
#30	25-60
#50	5-30
#100	0-10
#200	< 3.0

General Quality Results:

Bulk Specific Gravity SSD	ASTM C128	2.62
Absorption %	ASTM C128	0.9
Soundness MgSO4	ASTM C88	8

Available Locations:

Bromley Lakes
14585 Brighton Road
Brighton, Co 80601

Contact Information:

Wade Raitz, Sales Representative

wade.raitz@boral.com

Cell: 303-638-3598